


Reactive Brown GR

C.I. Reactive Brown 18

Light	:	6
Washing	Effect	: 3-4
	Stain	: 5
Perspiration Acidic	:	4
Bleaching Hypochlorite	:	1
Chlorinated Water	:	1
Dischargeability	:	Good
Solubility at 60°C	:	100 g/l

1% Cotton Dyeing
4% Cotton Dyeing
4% Cotton Printing
2% Discharge Printing



Reactive Black B 100%

C.I. Reactive Black 5

Light	:	5
Washing	Effect	: 4
	Stain	: 4-5
Perspiration Acidic	:	5
Bleaching Hypochlorite	:	1
Chlorinated Water	:	5
Dischargeability	:	Good
Solubility at 60°C	:	150 g/l

1% Cotton Dyeing
4% Cotton Dyeing
4% Cotton Printing
2% Discharge Printing

