








**Reactive Black GRP**  
C.I. Reactive Black

Light	:	5		
Washing		Effect	:	--
		Stain	:	4-5
Bleaching		Hypochlorite	:	1
		Peroxide	:	4
Perspiration (Acidic)		Effect	:	4
		Stain	:	4
Dischargeability	:	Good		
Solubility at 60°C	:	200 g/l		

1% Cotton Dyeing  
4% Cotton Dyeing  
1% Hosiery Dyeing  
4% Hosiery Dyeing



**Reactive Black GR**  
C.I. Reactive Black

Light	:	5		
Washing		Effect	:	--
		Stain	:	4-5
Bleaching		Hypochlorite	:	1
		Peroxide	:	5
Perspiration (Acidic)		Effect	:	4-5
		Stain	:	4
Dischargeability	:	Moderate		
Solubility at 60°C	:	100 g/l		

1% Cotton Dyeing  
4% Cotton Dyeing  
1% Hosiery Dyeing  
4% Hosiery Dyeing

