

Reactive Violet 5R 180%
C.I. Reactive Violet 5

Light	:	6-7
Washing	Effect	: 2-3
	Stain	: 5
Perspiration Acidic	:	4-5
Bleaching Hypochlorite	:	3-4
Chlorinated Water	:	4-5
Dischargeability	:	Moderate
Solubility at 60°C	:	140 g/l

1% Cotton Dyeing
4% Cotton Dyeing
4% Cotton Printing
2% Discharge Printing



Reactive Violet 5R 140%
C.I. Reactive Violet 5

Light	:	6-7
Washing	Effect	: 2-3
	Stain	: 5
Perspiration Acidic	:	4-5
Bleaching Hypochlorite	:	3-4
Chlorinated Water	:	4-5
Dischargeability	:	Moderate
Solubility at 60°C	:	100 g/l

1% Cotton Dyeing
4% Cotton Dyeing
4% Cotton Printing
2% Discharge Printing

