

### Reactive Violet Mix

C.I. Reactive Violet--

Light	:	4-5
Washing	:	4
Washing (Stain)	:	4-5
Perspiration	:	4-5
Substantivity	:	Medium
Dischargeability	:	Unsuitable
Hypochlorite	:	3-4
Solubility at 60°C	:	80 g/l

1% Cotton Dyeing  
4% Cotton Dyeing  
1% Cotton Printing  
4% Cotton Printing



### Reactive Violet MIX

C.I. Reactive Brown--

Light	:	5
Washing	:	4-5
Washing (Stain)	:	4-5
Perspiration	:	4
Peroxide	:	3-4
Substantivity	:	Medium
Dischargeability	:	Unsuitable
Hypochlorite	:	1
Solubility at 60°C	:	80 g/l

1% Cotton Dyeing  
4% Cotton Dyeing  
1% Cotton Printing  
4% Cotton Printing

